



FLOKPRINT 1950



VISCOSE
FLOCK



140°C



PEEL : HOT



Flock Blade 60°
Medium pressure



0.4mm



20 Sec

SPECIFICATIONS

APPLICATION

1. Printing and cutting

- Prepare the image on positive following the instruction of the printer manufacturer:
- Take care of the printing (45°C) and drying temperatures (50°C).
- Use the adequate printing profile (for instance, with Roland, select Colorip or Versawork, and then profile GENERIC VINYL 1, and we recommend to select the option MAX IMPACT).
- Remove the flock from the printer and wait for the complete drying of inks at room temperature, at least 4 hours.

2. Heat pressing

- Weed the excess material.
- Transfer the image by hand or if necessary with a strong tack tape (ATT 600).
- Position and heat press on a SEFA machine the image on the garment protected by a silicone paper at 160°C – 20 seconds – medium pressure.
- If you use it, peel the application tape off when hot.

FIBRES
THICKNESS:



White viscose flock media (velvet touch)
0.4 mm

CARRIER: Clear polyester



APPLIES ON

Cotton ● Polyester ● Acrylic and similar fibres.

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only
- Printable media are very sensitive: always handle with care and preferably with gloves.
- Always store the roll in a plastic bag protected from dust.
- It is important always using official inks from the printer manufacturer.

WASH

- Max 40°C
- Preferably inside out
- Do not bleach
- Tumble-dry approved
- Dry-cleaning unapproved

STORE

- Up to 1 year
- In a dry room (15-25°C)
- Away from sunlight
- In vertical position

Chemica
Heat transfers for textiles

NOTE: For best results, it is recommended to TEST prior to starting standard production